

data sheet



SPIRAL WOUND GASKETS

For flanged joints, heat exchangers, boiler handholes, manholes, and other high-temperature, high-pressure applications.



TYPE: 304L ASTM A240
Gauge: 99 (.007 x .210 x coil)
Heat No SE47197
Tag No 561473

CHEMICAL PROPERTIES

CARBON	0.0290
MANGANESE	1.5120
PHOSPHORUS	0.0300
SULPHUR	0.0020
SILICON	0.4270
CHROMIUM	18.0100
NICKEL	8.0500
MOLYBDENUM	
COPPER	
COBALT	
TITANIUM	
NITROGEN	0.0340
ALUMINUM	
IRON	
ZINC	
MAGNESIUM	

PHYSICAL PROPERTIES

YIELD: 61,100 PSI
TENSILE: 102,000 PSI
ELONGATION: 46%
HARDNESS 82.7 HRB
REDUCTION AREA: 0

ASTM A240 / A480
Tags: 561476, 561475, 561474

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. ARGCO and its agents cannot assume liability or responsibility for results obtained in the use of its product by persons whose methods are outside or beyond our control. It is the user's responsibility to determine the suitability of any of the products, methods of use, or preparation prior to use, mentioned in our literature. It is the user's responsibility to observe and adapt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.

**FOR MORE INFORMATION CALL ARGCO AT 1-800-854-1015
OR LOG ONTO WWW.ARGCO.COM**